

PERFORMANCE DATA CLEAR & TONED SINGLE GLAZED

Clear & Toned Glass

Walshs Glass provides a complete range of Clear & Toned glass products for all types of Residential & Commercial applications.

Glass has the advantage of being able to provide natural light and heat. Walshs Glass offers a large range of products that have been developed to improve comfort levels and visibility.

PRODUCT NAME	NOMINAL THICKNESS	VISIBLE		SOLAR		UV TRANS	U VALUE	SHGC	SHADING CO.	RW	
		Trans	Refl.	Trans	Refl.						
Float											
Clear	3	89	8	83	8	69	5.9	0.85	0.98	30	
	4	89	8	82	8	67	5.9	0.85	0.98	31	
	5	88	8	79	7	63	5.9	0.83	0.95	32	
	6	88	8	78	7	60	5.8	0.82	0.95	32	
	8	86	8	71	7	56	5.7	0.77	0.89	34	
	10	85	8	67	7	52	5.7	0.75	0.86	36	
	12	84	8	64	7	48	5.6	0.72	0.84	37	
	15	82	7	59	6	45	5.5	0.70	0.81	37	
Grey	19	80	7	55	6	41	5.4	0.67	0.78	40	
	4	56	6	55	6	30	5.9	0.66	0.77	31	
	5	47	6	47	5	23	5.8	0.61	0.71	32	
	6	42	5	42	5	19	5.8	0.58	0.67	32	
Green	10	27	5	31	5	12	5.7	0.51	0.59	36	
	12	21	4	25	5	9	5.6	0.47	0.55	37	
	4	82	8	58	6	38	5.9	0.68	0.79	31	
	5	79	7	51	6	32	5.9	0.63	0.74	32	
Bronze	6	77	7	47	5	27	5.8	0.61	0.71	32	
	10	63	6	29	5	11	5.7	0.49	0.57	36	
	4	61	7	60	6	28	5.9	0.70	0.81	31	
	5	54	6	52	6	22	5.9	0.64	0.74	32	
Laminate	6	49	6	48	5	19	5.8	0.62	0.71	32	
	10	34	5	36	5	9	5.7	0.54	0.63	36	
	Clear	6.38	87	8	72	7	<1	5.7	0.78	0.90	33
		6.76	86	8	71	7	<1	5.7	0.78	0.90	
8.38		87	8	72	7	<1	5.7	0.78	0.90	34	
10.38		86	8	66	7	<1	5.6	0.74	0.85	36	
Grey	12.38	85	8	65	7	<1	5.6	0.74	0.85	37	
	6.38	42	5	47	6	<1	5.7	0.61	0.71	33	
	8.38	41	5	46	5	<1	5.7	0.61	0.71	34	
	10.38	41	5	42	5	<1	5.6	0.59	0.67	36	
Bronze	12.38	41	5	41	5	<1	5.6	0.58	0.67	37	
	6.38	52	6	51	6	<1	5.7	0.64	0.74	33	
	8.38	52	6	50	6	<1	5.7	0.64	0.74	34	
	10.38	51	6	46	5	<1	5.7	0.61	0.70	36	
Green	12.38	51	6	45	5	<1	5.6	0.61	0.70	37	
	6.38	71	7	63	6	<1	5.7	0.72	0.83	33	
	8.38	71	7	62	6	<1	5.7	0.72	0.83	34	
	10.38	70	7	57	6	<1	5.6	0.69	0.79	36	
	12.38	69	7	56	6	<1	5.6	0.68	0.78	37	

Translucent	6.38	66	7	56	6	<1	5.7	0.67	0.78	33
	8.38	66	7	55	6	<1	5.7	0.67	0.77	34
	10.38	64	7	51	6	<1	5.6	0.64	0.74	36
	12.38	64	6	50	6	<1	5.6	0.64	0.73	37
Low Iron										
Clear	6	91	8	89	8	84	5.8	0.90	1.03	32
	10	90	8	87	8	81	5.7	0.89	1.02	36
High Performance Tones										
Evergreen	6	66	8	33	6	14	5.8	0.60	0.51	32
Super Green	6	67	6	34	5	13	5.8	0.52	0.61	32
Dark Grey	6	9	4	8	4	1	5.7	0.41	0.35	32
Super Grey	6	9	4	8	4	1	5.8	0.35	0.41	32
Super Blue	6	53	6	33	5	20	5.8	0.52	0.60	32

This data is measured using glass only and all care should be taken when evaluating our published data that the same environmental conditions have been used.

For the most up-to-date information, please visit our website.

All performance data is calculated using LBL Windows 5.2 software. NFRC 100-2001 conditions have been used.

Product Name – Where # appears, i.e. (#2), this identifies the position of the coated surface of the glass. Glass surfaces are counted from the exterior to the interior of the building.

Understanding these Chats

PRODUCT NAME	For more information on individual products ask your Walshs Sales Consultant.
NOMINAL THICKNESS	Identifies the glass thickness.
VISIBLE LIGHT TRANSMISSION	The percentage of visible light that passes directly through the glass. The higher the percentage, the more daylight gets through.
VISIBLE LIGHT REFLECTION	The percentage of visible light reflected toward the exterior.
SOLAR TRANSMISSION	The percentage of normal incident visible light and solar energy that passes directly through the glazing.
SOLAR REFLECTION	The percentage of normal incident visible light and solar energy reflected toward the exterior.
UV TRANSMISSION	The percentage of UV light transmitted measured in the light range of wave lengths shorter than 380 nanometres. A lower number is better.
U VALUE	The measure of the rate of heat gain or loss through glazing caused by environmental differences between indoor and outdoor air. The lower the value the better the insulation.
SHADING COEFFICIENT	The ratio of solar heat gain through glass relative to that through 3mm clear glass. A lower number indicates a better performance.
SHGC (SOLAR HEAT GAIN COEFFICIENT)	The proportion of total solar radiation that is transferred through glass in normal circumstances. A lower number indicates a better performance.

When you need to choose the right products the choice is clear

198 Bannister Road, Canning Vale, WA 6155

Tel: +61 8 9366 6609 Fax: +61 8 94552640

sales@walshsglass.com.au

www.walshsglass.com.au